

PRODUCT SPECIFICATIONS

Donhad758

Product Size: 125 mm

Sphericity: +/- 2% (Measured diagonally around the equator)

Hardness Surface: 58 HRc

Tolerance: +/- 2 HRc

Average Volumetric Hardness: 57.0 HRc (Typical)

Microstructure: Predominately Martensitic. Micro segregation towards the core of the product can cause variation in the hardness profile and is inherent.

Typical Analysis:

	C	Mn	Cr
Min	0.65	0.70	0.70
Max	0.75	1.20	1.20

Typical Hardness Profile:

