

PRODUCT SPECIFICATIONS

Donhad456

Product Size: 125 mm Nominal

Hardness Surface: 56 HRC

Tolerance: +/- 2 HRC

Average Volumetric Hardness: 56 HRC (Typical)

Microstructure: Martensitic with increasing volume fraction of pearlite/bainite towards the core of the product. Micro segregation is inherent.

Typical Analysis:

	C	Mn	Cr
Min	0.35	0.90	0.80
Max	0.45	1.40	1.40

Typical Hardness Profile:

