

PRODUCT SPECIFICATIONS

Donhad456

Product Size: 150 mm Nominal

Hardness Surface: 56 HRc

Tolerance: +/- 2 HRc

Average Volumetric Hardness: 54.0 HRc (Typical)

Microstructure: Martensitic with increasing volume fraction of pearlite/bainite towards the core of the product. Micro segregation is inherent.

Typical Analysis:

	C	Mn	Cr
Min	0.35	0.90	0.80
Max	0.45	1.40	1.40

Typical Hardness Profile:

