

PRODUCT SPECIFICATIONS

Donhad458

Product Size: 105 mm Nominal

Sphericity: +/- 2% (Measured diagonally around the equator)

Hardness Surface: 58 HRc

Tolerance: +/- 2 HRc

Average Volumetric Hardness: 56.5 HRc (Typical)

Microstructure: Predominately Martensitic. Micro segregation towards the core of the product can cause variation in the hardness profile and is inherent.

Typical Analysis:

	C	Mn	Cr
Min	0.35	0.90	0.80
Max	0.45	1.40	1.40

Typical Hardness Profile:

