

PRODUCT SPECIFICATIONS

Donhad658

Product Size: 105 mm Nominal

Sphericity: +/- 2% (Measured diagonally around the equator)

Hardness Surface: 58 HRc

Tolerance: +/- 2 HRc

Average Volumetric Hardness: 56.5 HRc (Typical)

Microstructure: Predominately Martensitic. Micro segregation towards the core of the product with increasing volume fraction of Bainite can cause variation in the hardness profile and in inherent.

Typical Analysis:

	C	Mn	Cr
Min	0.55	0.70	0.70
Max	0.70	1.10	1.10

Typical Hardness Profile:

