

PRODUCT SPECIFICATIONS

Product Size: 140 mm Nominal

Hardness Surface: 58 HRc

Tolerance: +/- 2 HRc

Average Volumetric Hardness: 56.5 HRc (Typical)

Microstructure: Predominately Martensitic. Micro segregation towards the core of the product can cause variation in the hardness profile and is inherent.

Typical Analysis:

	C	Mn	Cr
Min	0.55	0.90	0.90
Max	0.65	1.40	1.50

Typical Hardness Profile:

