

# PRODUCT SPECIFICATIONS

## **Donhad658**

**Product Size:** 140 mm Nominal

**Hardness Surface:** 58 HRc

**Tolerance:** +/- 2 HRc

**Average Volumetric Hardness:** 56.5 HRc (Typical)

**Microstructure:** Predominately Martensitic. Micro segregation towards the core of the product can cause variation in the hardness profile and is inherent.

### Typical Analysis:

	<b>C</b>	<b>Mn</b>	<b>Cr</b>
Min	0.55	0.90	0.90
Max	0.65	1.40	1.50

### Typical Hardness Profile:

