

# PRODUCT SPECIFICATIONS

## **Donhad662**

**Product Size:** 94 mm Nominal

**Sphericity:** +/- 2% (Measured diagonally around the equator)

**Hardness Surface:** 62 HRc

**Tolerance:** +/- 2 HRc

**Average Volumetric Hardness:** 57 HRc (Typical)

**Microstructure:** Predominately Martensitic. Micro segregation towards the core of the product with increasing volume fraction of Bainite can cause variation in the hardness profile and is inherent.

### Typical Analysis:

	<b>C</b>	<b>Mn</b>	<b>Cr</b>
Min	0.55	0.70	0.70
Max	0.70	1.10	1.10

### Typical Hardness Profile:

