

# PRODUCT SPECIFICATIONS

## **Donhad864**

**Product Size:** 64 mm Nominal

**Sphericity:** +/- 2% (Measured diagonally around the equator)

**Hardness Surface:** 64 HRc

**Tolerance:** +/- 2 HRc

**Average Volumetric Hardness:** 62.5 HRc (Typical)

**Microstructure:** Predominately Martensitic. Micro segregation towards the core of the product can cause variation in the hardness profile and is inherent.

### Typical Analysis:

	<b>C</b>	<b>Mn</b>	<b>Cr</b>
Min	0.75	0.70	0.40
Max	0.85	1.10	0.70

### Typical Hardness Profile:

