

PRODUCT SPECIFICATIONS

Donhad864

Product Size: 64 mm Nominal

Sphericity: +/- 2% (Measured diagonally around the equator)

Hardness Surface: 64 HRc

Tolerance: +/- 2 HRc

Average Volumetric Hardness: 62.5 HRc (Typical)

Microstructure: Predominately Martensitic. Micro segregation towards the core of the product can cause variation in the hardness profile and is inherent.

Typical Analysis:

	C	Mn	Cr
Min	0.75	0.70	0.40
Max	0.85	1.10	0.70

Typical Hardness Profile:

