

PRODUCT SPECIFICATIONS

Donhad1064

Product Size: 64 mm

Sphericity: +/- 2% (measured diagonally around the equator)

Hardness Surface: 62 HRc

Tolerance: +/- 2 HRc

Average Volumetric Hardness: 60.5 HRc (Typical)

Microstructure: Martensitic. Some pearlite at grain boundaries and higher volume fraction of retained austenite are inherent. Micro segregation towards the core of the product can cause variation in the hardness profile.

Typical Analysis:

	C	Mn	Cr
Min	0.90	0.60	0.30
Max	1.00	1.00	0.60

Typical Hardness Profile:

