

# PRODUCT SPECIFICATIONS

## Donhad1064

**Product Size:** 64 mm

**Sphericity:** +/- 2% (measured diagonally around the equator)

**Hardness Surface:** 62 HRc

**Tolerance:** +/- 2 HRc

**Average Volumetric Hardness:** 60.5 HRc (Typical)

**Microstructure:** Martensitic. Some pearlite at grain boundaries and higher volume fraction of retained austenite are inherent. Micro segregation towards the core of the product can cause variation in the hardness profile.

### Typical Analysis:

	C	Mn	Cr
Min	0.90	0.60	0.30
Max	1.00	1.00	0.60

### Typical Hardness Profile:

