

# PRODUCT SPECIFICATIONS

## Donhad1064

**Product Size:** 78 mm

**Sphericity:** +/- 2% (measured diagonally around the equator)

**Hardness Surface:** 64 HRC

**Tolerance:** +/- 2 HRC

**Average Volumetric Hardness:** 62.5 HRC (Typical)

**Microstructure:** Martensite + Retained Austenite. Increasing Bainite volume fraction towards the core of the product. Micro segregation towards the core of the product is inherent.

### Typical Analysis:

	C	Mn	Cr
Min	0.85	0.80	0.10
Max	1.00	1.50	0.40

### Typical Hardness Profile:

