

Donhad1064

Product Size: 78 mm

Sphericity: +/- 2% (measured diagonally around the equator)

Hardness Surface: 64 HRC

Tolerance: +/- 2 HRC

Average Volumetric Hardness: 62.5 HRC (Typical)

Microstructure: Martensite + Retained Austenite. Increasing Bainite volume fraction towards the core of the product. Micro segregation towards the core of the product is inherent.

Typical Analysis:

	C	Mn	Cr
Min	0.85	0.80	0.10
Max	1.00	1.50	0.40

Typical Hardness Profile:

